SYNTHESIS OF 3-AMINO-1-PHENYL-1<u>H</u>-PYRAZOLE-4,5-DIONE-4-ARYLHYDRAZONES AS FAST DYES

Tariq R. Sobahi^{*}, Mohamed A. Hassan and Zahra M. Alamshany Department of Chemistry, Faculty of Science, King Abdulaziz University, Jeddah-21589, P.O.Box 80203, Saudi Arabia. (Received 9th March 2005; Accepted 1st Aug. 2005)

ازدواج ديازو للمركب ٣–أمينو-١–فينيل-٢–بيرازولين-٥–أون مع أملاح آريل ديازونيوم في البريدين أعطى مركبات ٣–أمينو-١–فينيل-<u>H</u>1– بيرازول-٤,٥-داي اون-٤–آريل هيدرازونات التي تم استخدامها بصورة واسعة كأصباغ سريعة على منسوحات الصوف والحرير والقطن والبوليستر.

Diazocoupling of 3-amino-1-phenyl-2-pyrazolin-5-one (1) with aryldiazonium salts in pyridine afforded the coloured 3-amino-1-phenyl-1 \underline{H} -pyrazole-4,5-dione-4-arylhydrazones (2), which are, extensively, employed as fast dyes for wool, silk, cotton and polyesters.

INTRODUCTION

5-Pyrazolones are very important class of heterocycles due to their biological and pharmacological activities [1,2] which exhibit an antiinflammatory [3], herbicidal plant growth [4], fungicidal [5], bactericidal [5], plant growth regulator [4], antipyretic [6,7] and protein kinase inhibitors [8,9]. Also, they are used as key starting material for the synthesis of common commercial arylazopyrazolone dyes, which are used as good fastness dyestuffs for wool, cotton, silk, leather, rubber and synthetic polymers (Nylons).

On the other hand, many azopyrazolone dyes have been utilized as chromogenic reagents for colourimetric determinations [10,11] and as indicator for complexometric titrations [12]. Also, there are some arylazopyrazolone dyes having potent antimicrobial activities [13].

EXPERIMENTAL

All melting points reported are uncorrected. IR spectra were recorded using Perkin Elmer's Spectrum RXIFT-IR spectro-photometer (υ in cm⁻¹). The NMR spectra were recorded on Bruker Avance DPX400 spectrometer using TMS as internal standard (chemical shifts as δ values in ppm). The UV spectra were recorded by Shimadzu, Carry 50 (λ in nm, in absolute ethanol as solvent). Elemental analyses were preformed on Perkin Elmer 2400, series II micro-analyzer.

3-amino-1-phenyl-2-pyrazolin-5-one (1) is an Aldrich product, which is used without further purification.

General procedure:

Diazocoupling of 3-amino-1-phenyl-2-pyrazolin-5-one (1):

Synthesis of 3-amino-1-phenyl-1<u>H</u>-pyrazole-4,5-dione-4-arylhydrazones (2a-j):

The desired aromatic amine (0.015 mol) was treated with conc. HCl (5 ml) and cooled at 5°C in ice-bath. An aqueous cold solution of sodium nitrite (0.017 mol in 10 ml water) was added to the prepared aromatic amine hydrochloride to give the desired aromatic diazonium chloride solution which is added drop-wise during 30 min with stirring to an ice-cold solution of 3-amino-1phenyl-2-pyrazolin-5-one (1, 0.012 mol) in pyridine (50 ml). After complete addition the coloured precipitant was filtered, washed with hot water (3 x 25 ml), dried and crystallized from the proper solvent to give the coloured arylhydrazones (2a-j). The physical data of dyes (2) are listed in Table 1.

^{*} To whom all correspondence should be addressed; **E-Mail:** drtariq_s@hotmail.com

Compd. No.	Mol. Formula	m.p. (°C)	Solvent of cryst <u>on</u>	Elemental analysis Calculated/Found			
	(M.wt)	(Colour)	(yield %)	С	Н	Ν	
2a	2a $C_{15}H_{12}BrN_5O$ 204-206		Benzene	50.30	3.38	19.55	
	(358.19)	(brown)	(62)	50.17	3.33	19.42	
2b	$C_{15}H_{13}N_3O_2$	222-224	Ethanol	61.01	4.44	23.72	
	(295.30)	(red)	(91)	60.86	4.41	23.60	
2c	$C_{16}H_{15}N_5O_2$	168-170	Ethanol	62.13	4.89	22.64	
	(309.32)	(red)	(89)	61.97	4.83	22.53	
2d	C ₁₇ H ₁₅ N ₅ O ₂	201-203	Acetic acid	63.54	4.71	21.79	
	(321.33)	(brown)	(81)	63.37	4.66	21.65	
2e	$C_{16}H_{13}N_5O_3$	293-295	Dioxan	59.44	4.05	21.66	
	(323.31)	(violet)	(74)	59.32	4.00	21.54	
2f	$C_{19}H_{22}N_6O$	> 300	Ethanol	65.12	6.33	23.98	
	(350.42)	(brown)	(93)	65.01	6.30	23.79	
2g	$C_{21}H_{17}N_5O$	223-225	Ethanol	70.97	4.82	19.71	
_	(355.39)	(brown)	(90)	70.82	4.78	19.53	
2h	$C_{19}H_{15}N_5O_4S$	> 300	Ethanol	55.74	3.69	17.11	
	(409.42)	(orange)	(51)	55.63	3.64	16.97	
2i	$C_{20}H_{19}N_7O_2$	206-208	Ethanol	61.69	4.92	25.18	
	(389.41)	(brown)	(89)	61.54	4.87	25.03	
2j	$C_{18}H_{15}N_7O_2$	201-203	Ethanol	59.83	4.18	27.13	
-	(361.36)	(violet)	(53)	59.66	4.13	27.00	

Table 1: The physical data of 3-amino-1-phenyl-1H-pyrazole-4,5-dione-4-arylhydrazones (2a-j).

General methods of dyeing:

Method A: For arylhydrazones containing an acidic groups OH in **2b**, COOH in **2e** and SO₃H in **2h**.

Textile sample (2.0 g) was immersed in NaOH solution (5.0 %) for 30 min, then the sample was taken and immersed in the dyeing solution containing 0.5 g of arylhydrazone in 50.0 ml of NaOH (5.0 %). The mixture was left for 1h at 60°C. The solution was adjusted to pH 5 by adding glacial acetic acid with stirring for 15 min, then solution of 20.0 g of Na₂SO₄ in 250 ml water was added with stirring. The temperature of the mixture was raised to 90°C for 1h with stirring. Finally, the textile sample was taken, rinsed 3 times with 100 ml cold water and dried.

Method B: For arylhydrazones containing basic groups NH_2 in all synthesized arylhydrazones except **2b**, **2e** and **2h**.

Textile sample (2.0 g) was immersed in acetic acid (50 %) for 30 min. The dyeing solution was prepared by dissolving 0.5 g of arylhydrazone in 2.0 ml conc. HCl and then diluted to 50 ml by adding acetic acid (50 %). The textile sample was taken and immersed in the dyeing solution for 30 min at room temperature and 30 min at 60°C, then sodium sulphate (10 g) was added with stirring. The temperature of the mixture was raised and kept at 90°C for 30 min. The textile sample was taken and rubbed, then immersed in Na₂CO₃ solution (30%) and kept at 60°C for 30 min. The sample was taken, rinsed with water (3 x 100 ml) and then with hot water and dried.

All dyed fabrics by arylhydrazones (2a-j) are exposed to direct sunlight in open air for 15 days, washed by hot water and dried to give fabrics with bright, fast and stable colour. The UV spectra and the colour of the dyed textiles by the synthesized arylhydrazones (2a-j) are listed in Table 2.

J. Saudi Chem. Soc., Vol. 9, No. 3

Compd.	Ar	Method	UV	Fabric dyeing o				
No.		of dyeing	λ _{max} in nm	wool	silk	cotton p	oolyester	
2a	Br	В	354, 230, 215	pale yellow	pale yellow	weak yellow	weak yellow	
2b	но	А	415, 270, 230	deep yellow	yellow	pale yellow	weak yellow	
2c	MeO	В	420, 260, 235, 210	yellow	yellow	pale yellow	pale yellow	
2d	0 H ₃ C	В	395, 230, 215	buff	buff	buff	weak buff	
2e	ноос	А	395, 235, 225, 215	pale brown	weak brown	deep buff	buff	
2f	Et N	В	485, 270, 250, 235, 225	deep red	red	pink	deep pink	
2g		В	410, 260, 240, 225	yellow	yellow	weak yellow	pale yellow	
2h	SO ₃ H	А	420, 240	weak brown	orange	weak yellow	weak yellow	
2i	$Me \longrightarrow O$ $Me^{-N} \longrightarrow O$ I C_6H_5	В	430, 420, 405, 265, 255, 245, 230,220	yellow	deep yellow	pale yellow	pale yellow	
2j	H_2N N N C_6H_5	В	490, 285, 275, 250, 224	pale brown	brown	weak brown	beige	

Table 2: The UV spectral data	and dyeing textile o	of 3-amino-1-phenyl-1 <u>H</u> -pyrazole-4,5-dione-4-
arylhydrazones (2a-j).		


RESULTS AND DISCUSSION

In continuation to our interest in pyrazolone chemistry [14-18], we have reported here the synthesis of some new intensively

coloured 3-amino-1-phenyl-1 \underline{H} -pyrazole-4,5-ione-4-arylhydrazones (**2a-j**) that are used for dyeing of silk, wool, cotton and polyesters. The 3-amino-1phenyl-2-pyrazolin-5-one (**1**) existed in two tautomeric forms (I-II) due to their keto-enol

J. Saudi Chem. Soc., Vol. 9, No. 3


tautomerism, which are confirmed by IR absorption spectrum (Scheme 1).



A cold solution of aryldiazonium chlorides of primary aromatic amines, namely, 4bromoaniline, 4-hydroxyaniline, 4-methoxyaniline, 4-acetylaniline, 4-carboxyaniline, 4-N,N-

diethylaniline, 4-aminobiphenyl, 1-aminonaphthalene-4-sulphonic acid, 4-aminoantipyrine and 3amino-1-phenyl-2-pyrazolin-5-one (1), which are prepared by treatment of sodium nitrite solution with the hydrochloride solution of the previous primary aromatic amines are coupled at C4 with a cold solution of 3-amino-1-phenyl-2-pyrazolin-5one (1) in pyridine to give a tautomeric mixture of 3-amino-4-arylazo-1-phenyl-2-pyrazolin-5-one (2a-j).


The dyes may exist in four possible tautomeric forms, namely, two azo-keto forms A and D, the azo-enol form B and the hydrazone-keto form C as shown in Scheme 2. The deprotonation of the four tautomers (A-D) leads to a common anion.



Numerous investigations were carried out to establish the tautomeric structures of 4-arylazo-5-pyrazolones both in the solid state and in solution using a variety of spectroscopic techniques. The spectral data, generally, leads to the conclusion that the tautomeric equilibrium of the arylazo-pyrazolone dyes is in favor of the hydrazone form in the solid state and also in CHCl₃, DMSO and pyridine [19-21].

Our spectral data listed in **Table 3** proved that the 4-arylhydrazopyrazolones (C) are the existed structure of the all synthesized dyes due to their stabilization by interamolecular hydrogen bonding (**Scheme 3**). The colour of the synthesized arylhydrazopyrazolones (**2a-j**) ranges from yellow to deep red crystals (**Table 1**).


The structures of arylhydrazopyrazolones (2a-j) have been confirmed by IR and ¹H-NMR spectral data which are listed in **Table 3**.




- **c**) $Ar = C_6H_4$ -OCH₃,4**d**) $Ar = C_6H_4$ -COCH₃,4-
- **e**) Ar = C_6H_4 -COOH,4**f**) Ar = C_6H_4 -N(C_2H_5)₂,4-

g) Ar = $C_6H_5 - C_6H_4, 4$ -

h) Ar = 1-naphthyl-SO₃H,4-







Commit	Ar	IR (KBr) (<i>v</i> in cm ⁻¹)				¹ H-NMR	
Compd. No.		C=C, C=N	C=O	СН	OH, NH	in-nwik (δ in ppm)	
2a	Br	1564	1652	3069	3182 3302 3435	(CDCl ₃): 7.49 (m, 5H, Ar- <u>H</u>), 7.75 (d, 2H, Ar- <u>H</u>), 7.92 (s, 2H, Ar- <u>H</u>), 8.21-8.23 (d, 3H, N- <u>H</u> and N <u>H</u> ₂).	
2b	но-	1562	1692	3071	3376 3478	(CD ₃ COOD): 6.88 (d, 2H, Ar- <u>H</u>), 7.16 (t, 1H, Ar- <u>H</u>), 7.39 (m, 4H, Ar- <u>H</u>), 7.71 (d, 2H, Ar- <u>H</u>), 8.65-8.68 (m, 4H, O- <u>H</u> , N- <u>H</u> and N <u>H</u> ₂).	
2c	MeO	1571	1695	2928 3077	3168 3427	(CD ₃ COOD): 3.76 (s, 3H, OC <u>H</u> ₃), 6.93 (d, 2H, Ar- <u>H</u>), 7.14 (m, 1H, Ar- <u>H</u>), 7.34 (t, 2H, Ar- <u>H</u>), 7.47 (d, 2H, Ar- <u>H</u>), 7.71 (d, 2H, Ar- <u>H</u>), 8.41-8.43 (d, 3H, N- <u>H</u> and N <u>H</u> ₂).	
2d	H ₃ C	1583	1652 1674	2912 3065	3199 3330	(CD ₃ COOD): 2.63 (s, 3H, C <u>H</u> ₃), 7.22 (t, 1H, Ar- <u>H</u>), 7.43 (t, 2H, Ar- <u>H</u>), 7.66 (d, 2H, Ar- <u>H</u>), 7.78 (d, 2H, Ar- <u>H</u>), 8.08 (d, 2H, Ar- <u>H</u>), 8.50-8.52 (d, 3H, N- <u>H</u> and N <u>H</u> ₂).	
2e	ноос	1574	1629 1682	3061	3336 3439	(CD ₃ COOD): 7.21 (t, 1H, Ar- <u>H</u>), 7.43 (t, 2H, Ar- <u>H</u>), 7.57 (d, 2H, Ar- <u>H</u>), 7.76 (d, 2H, Ar- <u>H</u>), 8.13 (d, 2H, Ar- <u>H</u>), 9.51- 9.54 (m, 4H, O- <u>H</u> , N- <u>H</u> and N <u>H</u> ₂).	
2f	Et N-	1552	1649	2972 3070	3164 3441	(CDCl ₃): 1.13 (t, 6H, $2 \times C\underline{H}_3$), 3.39 (q, 4H, $2 \times N-C\underline{H}_2$), 7.13-7.94 (m, 9H, Ar- <u>H</u>), 8.55-8.57 (d, 3H, N- <u>H</u> and N <u>H</u> ₂).	
2g		1563	1637	3066	3180 3310 3484	(CD ₃ COOD); 7.16 (t, 1H, Ar- <u>H</u>), 7.29 (t, 1H, Ar- <u>H</u>), 7.38 (q, 4H, Ar- <u>H</u>), 7.60 (q, 4H, Ar- <u>H</u>), 7.66 (d, 2H, Ar- <u>H</u>), 7.72 (d, 2H, Ar- <u>H</u>), 8.39-8.42 (d, 3H, N- <u>H</u> and N <u>H</u> ₂).	
2h	SO ₃ H	1567	1629	3049	3339 3458	(CDCl ₃): 6.98 (b, 2H, N <u>H</u> ₂), 7.19-8.75 (m, 11H, Ar- <u>H</u>), 9.07 (b, 1H, N <u>H</u>), 9.16 (s, 1H, SO ₃ <u>H</u>).	
2i	Me Me ^{-N} N C ₆ H ₅	1562	1652	2968 3071	3356 3458	(CDCl ₃): 2.47 (s, 3H, C <u>H</u> ₃), 3.11 (s, 3H, N-C <u>H</u> ₃), 7.13-7.94 (m, 10H, Ar- <u>H</u>), 8.09-8.12 (d, 3H, N- <u>H</u> and N <u>H</u> ₂).	
2j	H ₂ N N N C ₆ H ₅	1552	1698	2877 3074	3114 3298 3464	(CD ₃ COOD): 3.80 (d, 1H, C4 [•] - <u>H</u>), 7.13–7.95 (m, 10H, Ar- <u>H</u>), 9.55-9.58 (m, 5H, N- <u>H</u> and 2x N <u>H₂</u>).	

Table 3: The spectral data of 3-amino-1-	phen	vl-1H-p	vrazole-4.5-dione-	4-arvlhvdrazones (2a-i).

J. Saudi Chem. Soc., Vol. 9, No. 3

Synthesis of 3-Amino-1-phenyl-1<u>H</u>-pyrazole-4,5-dione-4-arylhydrazones as Fast Dyes

REFERENCES

- S. Scheibye, A.A. El-Barbary, S.O. Lawesson, H. Fritz and G. Rihs, Tetrahedron, 38, 3753 (1982).
- [2] A. Weissberger and P. Wiley, "The Chemistry of Heterocyclic Compounds: Pyrazolinones, Pyrazolidones and Derivatives", John Wiley, New York (1964).
- [3] S.P. Hiremith, K. Rudresh and A.R. Saundan, Indian J. Chem., **41B** (2), 394 (2002).
- [4] S. Joerg, G. Reinhold, S. Otto, S.H. Joachim,
 S. Robert and L. Klaus, Ger Offen, 04 Feb. 1988, DE 3, 625, 686 (Cl C07D 231/22),
 [C.A., 108, 167465 (1988)].
- [5] P.N. Dhol, T.E. Achary and A. Nayak, J. Indian Chem. Soc., 52, 1196 (1975).
- [6] F.R. Souza, V.T. Souza, V. Ratzlaff, L.P. Borges, M.R. Olivera and H.G. Bonacorso, Eur. J. Pharma, 45 (2), 141 (2002).
- [7] J.R. McTavish, Aspirin and Related Drugs, 25 (2004).
- [8] J. Singh and R. Tripathy, PCT Int. Appl., 138 (2001).
- [9] M. Abdallah, Materials Chemistry and Physics, **82**, 786 (2003).

- [10] H. Miyara, Bull. Chem. Soc. Jpn, 36, 382 (1963). 37, 426 (1964). 40, 1875 and 2815 (1967).
- [11] Toeik, Bull. Chem. Soc. Jpn, 38, 1050 (1965).
- [12] H. Khalifa and R.M. Issa, Egypt J. Chem., 17, 581 (1974).
- [13] D. Azarifar and M. Shaebanzadeh, Molecules, 7, 885 (2002).
- [14] A. El-Shekeil, A. Babaqi, M.A. Hassan and S. Shiba, Heterocycles, 27, 2577 (1988).
- [15] M.A. Hassan, M. El-Kasaby and M.K. Abou El-Regal, Phosphorus, Sulfur and Silicon, 104, 15 (1995).
- [16] M.A. Hassan and D. Doepp, Heterocycles, 45, 451 (1997).
- [17] T.R. Sobahi, M.A. Hassan and Z.M. Alamshany, The Second Saudi Science Conference, King Abdulaziz University, 15-17 March (2004).
- [18] T.R. Sobahi, Indian J. Chem., 44B, (2005), In press.
- [19] N. Ertan, Dyes and Pigments, 44, 41 (2000).
- [20] H. Yasuda and H. Midorikawa, J. Org. Chem., **3**, 1722 (1966).
- [21] F. Karci and N. Ertan, Dyes and Pigments, 55, 99 (2002).

J. Saudi Chem. Soc., Vol. 9, No. 3

Tariq R. Sobahi, Mohamed A. Hassan and Zahra M. Alamshany